

Product range

ETG[®] steels are available in various categories, finishes and sizes:

Steel category	Processes	Size range [mm]	Tolerance
ETG [®] 88 round	drawn	≥ 5,0 – ≤ 20,5	h9
		> 20,5 – ≤ 64,0	h11
		> 64,0 – ≤ 114,3	h12
	ground	≥ 5,0 – ≤ 100,0	≥ IT6
ETG [®] 100 round	drawn	≥ 6,0 – ≤ 64,0	h11
		> 64,0 – ≤ 70,8	h12
	ground	≥ 6,0 – ≤ 70,8	≥ IT6
ETG [®] 88 hexagonal	drawn	SW 13 – 27	h11

- Bar lengths: 3 - 6,5 m
- Colour coding: ETG[®] 88 white end face, ETG[®] 100 gold end face
- Bright-turned and bright-turned/ground to special order
- Regular sizes are available from stock
- 100% eddy current tested acc. to surface class 3 of EN 10277-1
- Other categories to meet special requirements (e.g. mechanical properties) are available to special order.

Chemical composition (ETG[®] 88/100, analysis by mass in %)

Element	C	Si	Mn	P	S
min.	0,42	0,10	1,35		0,24
max.	0,48	0,30	1,65	0,04	0,33

The analysis corresponds to SAE1144 and 44SMn28 (1.0762).
Piece analysis and melt analysis may vary according to EN 10087, table 2.

Mechanical properties (Typical values)

Static			ETG [®] 88	ETG [®] 100
Dimensions	Ø	mm	5,0 – 114,3	6,0 – 70,8
Proof stress	drawn	R _{p0,2}	≥ 685	≥ 865
	ground		≥ 630	≥ 800
Tensile strength	R _{p0,2}	N/mm ²	800 – 950	960 – 1100
Ultimate elongation	A ₅	%	≥ 7	≥ 6
Reduction of area	Z	%	ap. 30	ap. 20
Elastic modulus		N/mm ²	ap. 200 000	ap. 200 000

Tensile strength (transverse)	R_m	N/mm ²	ca. 600	ca. 720
Hardness				
HRC			ca. 28	ca. 32
HB 30			ca. 280	ca. 320
Lateral shear strength	T_s	N/mm ²	ca. 510	ca. 590
Torsional shear strength	T_t	N/mm ²	ca. 440	ca. 540
Notched impact energy	AV_{RT}	J	ca. 25	ca. 10

Dynamic

Tension/compression	σ_w	N/mm ²	ca. 350	ca. 370
Pulsating	σ_{sch}	N/mm ²	ca. 250	ca. 270
Reverse bending	σ_{bw}	N/mm ²	ca. 390	ca. 420
Torsional reversal	T_{tw}	N/mm ²	ca. 195	ca. 225
Torsional pulsating	T_{sch}	N/mm ²	ca. 345	ca. 390

For further info on our product range of tool steel, stainless steel and Engineering steel please visit www.swisssteelgroup.com

28.06.23 Rev. N°1

Discover our Green Steel portfolio on www.swissgreensteel.com

The information and data contained in this document represent standard or average values and do not constitute a warranty or guarantee of minimum or maximum values. The information contained in our material test certificates is solely authoritative. Application recommendations for the materials described in this document are provided for guidance only to enable the reader to make their own decisions and do not constitute an express or implied warranty or guarantee that a material is suitable for a particular application.

Subject to change, errors and printing mistakes. The desired performance characteristics are only binding if they are exclusively agreed upon at the time of contract conclusion.

Swiss Steel Group
 Steeltec AG / Steeltec GmbH:
 Emmenbrücke / Düsseldorf
info.engineering@swisssteelgroup.com